

HDCAM



Continually-developed metal tape technology

Strengthened binder achieves 50% increase in cross-linking density.

Dropout prevention and archival stability using alumina-silica particle coating

Extended head life with specially developed lubricants

Controlled surface roughness increases S/N ratio

Cleaning Tape: BCT-5CLN

General Characteristics

Master Carton Quantity (piece)	BCT-124HDL: 10 BCT-94HDL: 10 BCT-64HDL: 10 BCT-34HDL: 10 BCT-40HD: 50 BCT-32HD: 50 BCT-22HD: 50 BCT-6HD: 50
Master Carton Weight (kg)	BCT-124HDL: 8.3 BCT-94HDL: 7.8 BCT-64HDL: 7.3 BCT-34HDL: 6.8 BCT-40HD: 17.3 BCT-32HD: 16.7 BCT-22HD: 15.8 BCT-6HD: 14.9
Playing time (min)	BCT-124HDL: 124 BCT-94HDL: 94 BCT-64HDL: 64 BCT-34HDL: 34 BCT-40HD: 40 BCT-32HD: 32 BCT-22HD: 22 BCT-6HD: 6
	BCT-124HDL: 732 BCT-94HDL: 557

Tape length (m)	BCT-64HDL: 382 BCT-34HDL: 206 BCT-40HD: 241 BCT-32HD: 195 BCT-22HD 136 BCT-6HD: 43
-----------------	---

Weight (g)	BCT-124HDL: 780 BCT-94HDL: 728 BCT-64HDL: 677 BCT-34HDL: 630 BCT-40HD: 308 BCT-32HD: 295 BCT-22HD: 277 BCT-6HD: 260
------------	--

Magnetic Properties

Intrinsic coercivity (kA/m)	132.0
Retentivity (mT)	290.0
Squareness (Br/Bm)	0.83

Physical Properties

Thickness: backcoating (μm)	1.0
Thickness: base (μm)	10.0
Thickness: magnetic layer (μm)	3.0
Thickness: total (μm)	14.0
Width (mm)	12.65

Video and Audio Performance

Recording Density (Mb/inch ²)	0.0
RF Playback output (dB)	0.0
C/N	0.0

